

FAKTABLAD



SUNBRELLA DEAUVILLE

Dynväv

EGENSKAPER	VÄRDEN		ENHET	STANDARDER
	VARP	VÄFT		

ALLMÄNNA EGENSKAPER

Sammansättning	100% Sunbrella solution dyed acrylic		
Slutbehandling	Stain-resistant treatment: exclusive Glen Raven formulation. Does not contain PFOS (perfluorooctanyl sulphonate).		
Bindning	Natté 3/3		ISO 7211-1
Vikt	360		g/m ² ISO 2286-1
Tygbredd	142		cm EN 1773

TYGETS SLITSTYRKA

Oljeavvisande behandling	6		class /8	ISO 14419
Brottstyrk	200	130	daN	ISO 13934-1
Rivhållfasthet	> 13.5	> 13.5	daN	ISO 13937-1
Brottöjning	33	25	%	ISO 13934-1
Schmerber-test	240		mm	ISO 811
Spray-test	5		class /5	ISO 4920
Stabilité au lavage (40 °C°)	1	1	%	ISO 5077
Slitage (Martindale)	10 000 - 38 000		Nb cycles	ISO 12947-2
Luftgenomtränglighet	140 (+/- 20%)		l/m ² /s	ISO 9237

FÄRGERS BESTÄNDIGHET

Färgers UV-beständighet	7/8		class /8	ISO 105 B02
Färgers väderbeständighet	7/8		class /8	ISO 105 B04
Färgers torrfröttering	5		class /5	ISO 105X12
Färgers våtfröttering	5		class /5	ISO 105X12
Färgers au lavage (40 °C°)	5		class /5	ISO 105 C06

ANVÄNDNING

Skärlängd	50		lm	
Rekommenderad användning	Cushion and upholstery			
Garanti	5		År	

The values for this product may have a variation of +/-5%.

Stitch test carried out with 32pts/100mm, a 110 needle, and a 100% Pes 74 tex thread.

Dickson - Constant

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com

SUNACRYL[®]
OUTDOOR FIBRE
by DIC[®]SON[®]

FINISHING
CLEANGARD[®]
OUTDOOR TREATMENT
by DIC[®]SON[®]

