

## FAKTABLAD



# SUNBRELLA DUPIONE

## Dynväv

EGENSKAPER	VÄRDEN		ENHET	STANDARDER
	VARP	VÄFT		

### ALLMÄNNA EGENSKAPER

Sammansättning	100% Sunbrella solution dyed acrylic			
Slutbehandling	Stain-resistant treatment: exclusive Glen Raven formulation. Does not contain PFOS (perfluorooctanyl sulphonate)			
Bindning	Canvas			ISO 7211-1
Vikt	320		g/m <sup>2</sup>	ISO 2286-1
Tygbredd	137		cm	EN 1773

### TYGETS SLITSTYRKA

Resistens mot eld	class 1			NF P 92 503
Oljeavvisande behandling	5			class /8 ISO 14419
Brottstyrk	150	80	daN	ISO 13934-1
Rivhållfasthet	11.5	> 13.5	daN	ISO 13937-1
Brottöjning	33	26	%	ISO 13934-1
Schmerber-test	100			mm ISO 811
Spray-test	5			class /5 ISO 4920
Stabilité au lavage (40 °C°)	-1	-0.1	%	ISO 5077
Slitage (Martindale)	10 000			Nb cycles ISO 12947-2
Luftgenomtränglighet	75			l/m <sup>2</sup> /s ISO 9237
Sömstyrka	55	49	daN	ISO 13935-1



### FÄRGERS BESTÄNDIGHET

Färgers UV-beständighet	7/8	class /8	ISO 105 B02
Färgers väderbeständighet	7/8	class /8	ISO 105 B04
Färgers torrrottering	5	class /5	ISO 105X12
Färgers våtrottering	5	class /5	ISO 105X12
Färgers au lavage (40 °C°)	5	class /5	ISO 105 C06

### ANVÄNDNING

Skärlängd	50	lm	
Rekommenderad användning	Cushion, parasol and upholstery		
Garanti	5	År	

The values for this product may have a variation of +/-5%.<br />

Stitch test carried out with 32pts/100mm, a 110 needle, and a 100% Pes 74 tex thread.

### Dickson - Constant

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - [www.dickson-constant.com](http://www.dickson-constant.com)