

## FAKTABLAD



# SUNBRELLA KYOTO

## Dynväv

EGENSKAPER	VÄRDEN		ENHET	STANDARDER
	VARP	VÄFT		

### ALLMÄNNA EGENSKAPER

Sammansättning	100% Sunbrella solution dyed acrylic			
Slutbehandling	Stain-resistant treatment: exclusive Glen Raven formulation. Does not contain PFOS (perfluorooctanyl sulphonate)			
Bindning	Double cloth			ISO 7211-1
Vikt	550		g/m <sup>2</sup>	ISO 2286-1
Tygbredd	137		cm	EN 1773

### TYGETS SLITSTYRKA

Resistens mot eld	class 1			NF P 92 503
Oljeavvisande behandling	5			class /8 ISO 14419
Brottstyrk	175	190	daN	ISO 13934-1
Rivhållfasthet	13	12	daN	ISO 13937-1
Brottöjning	33	30	%	ISO 13934-1
Schmerber-test	50			mm ISO 811
Spray-test	4			class /5 ISO 4920
Stabilité au lavage (40 °C°)	-1	-0.5	%	ISO 5077
Slitage (Martindale)	8 000			Nb cycles ISO 12947-2
Luftgenomtränglighet	250			l/m <sup>2</sup> /s ISO 9237
Sömstyrka	50	40	daN	ISO 13935-1

**SUNACRYL<sup>®</sup>**  
OUTDOOR FIBRE  
by DIC<sup>®</sup>SON<sup>®</sup>

FINISHING  
**CLEANGARD<sup>®</sup>**  
OUTDOOR TREATMENT  
by DIC<sup>®</sup>SON<sup>®</sup>



### FÄRGERS BESTÄNDIGHET

Färgers UV-beständighet	7/8	class /8	ISO 105 B02
Färgers väderbeständighet	7/8	class /5	ISO 105 B04
Färgers torrrottering	5	class /5	ISO 105X12
Färgers våtrottering	5	class /5	ISO 105X12
Färgers au lavage (40 °C°)	5	class /5	ISO 105 C06

### ANVÄNDNING

Skärlängd	30	lm	
Rekommenderad användning	Cushion and upholstery		
Garanti	3	År	

The values for this product may have a variation of +/-5%.  
Stitch test carried out with 32pts/100mm, a 110 needle, and a 100% Pes 74 tex thread.

### Dickson - Constant

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France  
Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - [www.dickson-constant.com](http://www.dickson-constant.com)